


Description:

The Everlast Metals ASL-150 is a standing seam roof system that offers the designer the classical look of a traditional standing seam panel and the high performance of an architectural system. Available with a 1 1/2" seam height manufactured with optional minor ribs or striations, and its concealed clip to allow for fluid thermal movement.



General Use & Method of Application:

Everlast Metals ASL-150 panels must be installed in a sequential pattern. Application of a Everlast Metals approved underlayment prior to panel installation is recommended when installed over a solid substrate.

- Install in accordance with industry-recognized sheet metal practices.
- Cut, form, and fasten using conventional hand or power tools.
- For best results cutting tool edges should be kept sharp, clean, properly dressed, and closely aligned.
- Fabrication and erection can be accomplished with strippable plastic film in place. Film should be removed from areas of concealed or joined pieces.

Storage:

Everlast Metals metal panels should be stored in a well-ventilated, dry place where no moisture can contact them. Moisture (from rain, snow, condensation, etc.) trapped between layers of material may cause water stains or white rust, which can affect the service life of the material and will detract from its appearance. If outdoor storage cannot be avoided, protect the panels with a ventilated canvas or waterproof paper cover. Do not use plastic, which can cause condensation. Keep the material off the ground in an inclined position with an insulator such as wood. Protective film may degrade or become brittle with long-term exposure to direct sunlight.

Precautions:

- Protective film may degrade or become brittle with exposure to direct sunlight. Therefore, it must be removed immediately.
- Product should not be used in areas of high abrasion or where it is subject to mechanical damage.
- Product is pre-finished material; care must be exercised during fabrication and erection to avoid surface damage.
- Everlast Metals recommends a minimum bend radius of 2T for .032 materials. Anything less than these minimum bend radii can cause crazing to the material.
- Attention should be paid to good house-keeping practices.
- Avoid dragging sheets over surfaces which may scratch or mar the finish.
- For general sheet metal use in building applications.
- Do not cut with power saws or abrasive blades.

Manufacturing Locations:

Lebanon, PA • Howe, IN • Bridgton, ME

Product Size:

| | |
|-----------------------|-----------------------|
| Panel Widths: | 12", 16", 20", Custom |
| Overall Coverage: | + or - 1/4" |
| Seam Height: | 1.5" |
| Minimum Panel Length: | 4' |
| Maximum Panel Length: | 40', Custom |

Product Data:

| | |
|-------------------------|----------|
| Minimum Slope: | 3:12 |
| Tapered Panels: | Yes |
| Radiused Panels: | No |
| Stiffening Ribs: | Optional |
| Striations: | Optional |
| Standard Panel Surface: | Smooth |

Technical Information:

| | |
|-------------------------|---------------------------|
| Uplift Resistance: | UL 580 Class 90 |
| Structural Performance: | ASTM E330, E72, and E1592 |
| Air Infiltration: | ASTM E283 and E1680 |
| Water Penetration: | ASTM E331 and E1646 |
| Impact Resistance: | PA 201 |
| Wind-Driven Rain: | TAS 100 |

Note: Testing is not applicable for all combinations of substrates, materials, and dimensions. All construction assemblies must be installed in accordance with the testing assembly. Please refer to the Product Specifications on the Everlast Metals website for tested assemblies and code listings.

| Material and Thickness: | Metal Specification: | Available Finishes: |
|--|---|--|
| Aluminum 0.032" (0.81 mm) | Base Metal: Aluminum Thermal Expansion: 12.6×10^{-6} in/in/F° ($22.2 \text{ m/m.K} \times 10^{-6}$) | Synergy™ Fluropon® Unpainted/Mill Finish |
| Galvanized Steel 26 ga. (0.48 mm) 24 ga. (0.64 mm) 22 ga. (0.75 mm) | Mod. Of Elasticity: $10.0 \times 10^3 \times \text{KSI}$ (68.9 MPa) Base Metal: AISA-G90 Galvanized Steel Thermal Expansion: 06.7×10^{-6} in/in/F° ($13.9 \text{ m/m.K} \times 10^{-6}$) Mod. Of Elasticity: $29.0 \times 10^6 \times \text{KSI}$ (200 GPa) | G90- Clear Acrylic Coated Synergy™ Fluropon® |
| Galvalume® Steel 26 ga. (0.46 mm) 24 ga. (0.64 mm) | Base Metal: AZ50 Galvalume® Steel Thermal Expansion: 06.7×10^{-6} in/in/F° ($13.9 \text{ m/m.K} \times 10^{-6}$) Mod. Of Elasticity: $29.0 \times 10^6 \times \text{KSI}$ (200 GPa) | Acrylume®- Clear Acrylic Coated Synergy™ Fluropon® |

Please contact Everlast Metals (800) 418-5057 for further information.

This sheet is meant to highlight Everlast Metals products and specifications and is subject to change without notice. Everlast Metals takes responsibility for providing quality materials which meet published Everlast Metals product specifications. Neither Everlast Metals nor its representatives practice architecture. Everlast Metals offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. Everlast Metals accepts no liability for structural failure of resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Everlast Metals representative is authorized to vary this disclaimer.